

09/776,278

P-3724-2-F1-C1-C1

IN THE SPECIFICATION

Please replace the paragraph beginning at page 24, line 23 with the following rewritten paragraph:

DI Other soft, relatively low modulus non-ionomeric thermoplastic elastomers may also be utilized to produce the outer cover layer as long as the non-ionomeric thermoplastic elastomers produce the playability and durability characteristics desired without adversely effecting the enhanced spin characteristics produced by the low acid ionomer resin compositions. Preferably, the non-ionomeric thermoplastic elastomers have a Shore D hardness of 64 or less. These include, but are not limited to thermoplastic polyurethanes such as: Texin[®] thermoplastic polyurethanes from Mobay Chemical Co. and the Pellethane[®] thermoplastic polyurethanes from Dow Chemical Co.; Ionomer/rubber blends such as those in Spalding U.S. Patents 4,986,545; 5,098,105 and 5,187,013; and, Hytrel[®] polyester elastomers from DuPont and Pebax[®] polyetheramides from Elf Atochem S.A.

D